

♠ ACUMEN SCIENTIFIC SDN. BHD. (514926-V)

Plot No. 256, Tingkat Perusahaan 5, Kawasan Perindustrian Perai 2, 13600 Perai, Penang, Malaysia Tel: +604-388 3609 Fax: +604-388 3708

Certificate No

Date Issue

Sample Log Code

Sample Received Date : 31-Oct-2013

Complete Analysis Date: 11-Nov-2013

Email: inquiry@acumen.com.my Website: www.acumen.com.my

CERTIFICATE OF ANALYSIS

MAIDAMAX (M) SDN BHD Lot. 10-13, Jalan PKNK 1/2,

Kawasan Perusahaan Sungai Petani, 08000 Sungai Petani, Kedah, Malaysia.

Tel: 04-4414 644 Fax: 04-4414 649

Attn: Mr Samuel Saw

Sample Description : Natural Rubber Teat

Quantity: 100g

Trace No: 2013/10/102

Analysis results

Parameter	Units	Analysis Result	Standard Method/Technique/Equipment Used	Spec.
Evaporative residue in 4% Acetic acid	mg/L	7.4	GB 4806.2	120
Evaporative residue in water	mg/L	28.5	GB 4806.2	30
Consumption of Potassium Permaganate Solution	mg/L	6.5	GB 4806.2	30
Lead	mg/L	ND(<0.1)	Extraction with acetic acid 4 %, 60 deg C for 2hr, then followed by ICP-OES	1.0
Zinc	mg/L	2.5	Extraction with acetic acid 4 %, 60 deg C for 2hr, then followed by ICP-OES	30

Remark: # Test Condition: 10g of sample soaked with 200ml of acetic acid, then determined by ICP-OES. # Spec. = Compliance specification according to GB 4806.2-94 standard.

Teem Chin Mean Manager M.Sc., AMIC, A/2152/4620/04

: CN/nCML0233/1013

: nCML0256/1013

: 11-Nov-2013

Page 1/1